

## TFO LightBend Plus® (G.657.A2)

Based on the optimum RIP design, TFO LightBend Plus® fibre is a full spectrum fibre with zero water peak, low attenuation and excellent uniformity, low PMD, excellent macrobending loss at minimum radius 7.5mm, superior and stable geometrical size control level, this full spectrum fibre is applicable to transmission system operating over the entire wavelength from 1260nm to 1625nm. TFO LightBend Plus® fibre meets or exceeds the ITU-T Recommendation G.657.A2 and IEC 60793-2-50 type B6.a2 Optical Fibre Specification and completely compatible with traditional ITU-T G.652.D and IEC 60793-2-50 type B1.3 fibre, widely used in all types of optical fibre cables especially tight-buffer cable and rubber-insulated cable.

Characteristics	Conditions	Parameters	Unit
<b>Optical properties</b>			
Attenuation Coefficient	1310 nm 1285-1330 nm 1383 nm (after hydrogen aging) 1490 nm 1550 nm 1525 - 1575 nm 1625 nm	≤ 0.34 ≤ 0.37 ≤ 0.31 ≤ 0.23 ≤ 0.20 ≤ 0.21 ≤ 0.22	dB/km dB/km dB/km dB/km dB/km dB/km dB/km
Mode Field Diameter(MFD)	1310 nm 1550 nm	8.7 ± 0.4 9.9 ± 0.5	μm μm
Cut-Off Wavelength Cable Cut-Off		≤ 1260	nm
Chromatic Dispersion Zero Dispersion Wavelength Zero Dispersion Slope		1300 - 1324 ≤ 0.090	nm ps/nm²/km
Dispersion Coefficient	1285 - 1339 nm 1550 nm 1625 nm	≤  3.4  ≤ 18.0 ≤ 22.0	ps/nm/km ps/nm/km ps/nm/km
Polarisation Mode Dispersion PMD Coefficient	Uncabled fibre PMD link design value	≤ 0.10 ≤ 0.06	ps/√km ps/√km
Point Discontinuity	1310 nm 1550 nm	≤ 0.05 ≤ 0.05	dB dB
Effective Group Refractive Index	1310 nm 1550 nm 1625 nm	1.4671 1.4675 1.4680	
<b>Geometrical Properties</b>			
Core Non-circularity		≤ 6	%
Cladding Diameter		125.0 ± 0.5	μm
Core/Cladding Concentricity Error		≤ 0.5	μm
Cladding Non-Circularity		≤ 0.7	%
Coating Diameter		242 ± 5	μm
Coating/Cladding Concentricity Error		≤ 8	μm
<b>Mechanical properties</b>			
Proof Test	Fibre strain Fibre load Stress	≥ 1 ≥ 9 ≥ 100	% N kpsi
Dynamic Stress Corrosion Susceptibility Factor $n_d$	Unaged Aged (30 days @ 85°C, 85% R.H.)	≥ 20 ≥ 20	
Macro Bending Sensitivity	10 turns of 15 mm radius, 1550nm 10 turns of 15 mm radius, 1625 nm 1 turns of 10 mm radius, 1550 nm 1 turns of 10 mm radius, 1625 nm 1 turns of 7.5 mm radius, 1550 nm 1 turns of 7.5 mm radius, 1625 nm	≤ 0.03 ≤ 0.1 ≤ 0.1 ≤ 0.2 ≤ 0.2 ≤ 0.5	dB dB dB dB dB dB
Coating Strip Force	Peak value	1.3 - 8.9	N
Fibre Curl		≥ 4	m
<b>Environmental Properties</b>			
Accelerated Ageing (30days @ 85°C,85% R.H.)	Induced attenuation (1310 and 1550 nm)	≤ 0.05	dB/km
Dry heat aging (30days @ 85°C)	Induced attenuation (1310 and 1550 nm)	≤ 0.05	dB/km
Temperature Cycling (-60°C- +85°C)	Induced attenuation (1310 and 1550 nm)	≤ 0.05	dB/km
Water Soak (30 days @ 23°C)	Induced attenuation (1310 and 1550 nm)	≤ 0.05	dB/km